

NST 309LT

AWS A5.22/A5.22M E309LT 0-4

NS-EN ISO 17633-A: T 23 12 L R M21 3

EN ISO 9606-1: FM5



Flux cored wire mainly for flat position and fillet welding of corrosion resistant materials against carbon steels and for cladding carbon steels.

General description:

NST 309LT is a rutile flux cored wire for flat position (PA) and fillet welding (PB and PC) of corrosion resistant materials such as AISI 304 etc. against carbon steel.

The flux cored wire uses an Argon/CO₂ mixed shielding gas.

This ensures a user friendly and stable welding arc, less spatter, good visual bead appearance and smooth transition to the parent materials.

NST 309LT has a slag freezing system which is slightly slower than wires designed for positional welding.

This makes this wire suitable for flat position and fillet welds.

It is also suitable for use with ceramic backing for single sided welding.

The wire's composition ensures weld metal equivalent AISI 304 in the first layer of the cladding process.

Welding positions:



Welding current:

DC+

Gas flow:

15-23 l/min.

Typical chemical composition of all-weld-metal:

C	Si	Mn	P	S	Cu	Ni	Cr	Mo	
0.028	0.77	1.25	0.023	0.002	0.13	12.77	24.81	0.13	

Shielding gas:

Argon+18-25% CO₂.

Typical mechanical properties of all-weld-metal:

Yield and Tensile Strengths				
Yield Mpa(Rp0.2)	Tensile Mpa(Rm)	Elongation %		
425	550	36		

Guidance - Ampere (DC+):

Electrode diameter			
Ampere / Volt			

Packaging information:

1,2mm x 12,5kg

Approvals:

CE

Reference / date:

NST 309LT,
English, 12.09.2025.

Perfect Welding

www.nst.no